

STUCCOFACILE

ПАСТООБРАЗНАЯ БЫСТРОСОХНУЩАЯ ШТУКАТУРКА НА ОСНОВЕ МИКРОСФЕР, ЛЕГКАЯ В НАНЕСЕНИИ

code 9560019

ОПИСАНИЕ

STUCCOFACILE - штукатурка готового состава пастообразная для внутренних и внешних работ на основе микросфер стекла; используется для нанесения на настенные и деревянные поверхности. Легка в нанесении, быстро высыхает, позволяет реализовать толстый слой без выемок и трещин. Не желтеет, отлично прилегает к любой поверхности и быстро поверх покрывается синтетическими красками на водо-дисперсионном составе. Особенно предназначена для штукатурки оставшихся отверстий от строительных лесов. На внешнюю поверхность штукатурка должна быть покрыта как минимум в два слоя водоэмульсионной краской.

ОСНОВА НАНЕСЕНИЯ

May be applied over:

- Lime mortar and cement-lime mortar plasters; air-hardening and fine sand plasters, new or previously painted.
 - Gypsum bases such as panels, dividing and partition walls.
 - Interior wooden supports prior to painting.
- STUCCOFACILE is a primer and must be paint over with a top coat finishing system.

ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ

Binder: Vinyl-versatic copolymer in a watery emulsion.
-Volumic mass UNI 8910: 0.35 ± 0.05 kg/l
-Appearance: white paste
-Drying (at 25°C and 65% R.H.): varies depending on thickness applied; a 1 cm layer of stucco to recoat after 30 min.
PAINTING: to recoat with water-based paints and all water-soluble enamel paints.

ПОДГОТОВКА ПОВЕРХНОСТИ

Plaster surfaces:

- Check that the base has been seasoned for at least 28 days.
- Check the condition of the base. The surface must be consistent. If not, reapply or consolidate with appropriate products.
- Remove any efflorescence with a brush or by washing.
- If there is old paint, remove peeling paint; completely remove thick layers of lime or tempera paint by wetting the surface thoroughly and scraping it, or using a jet of water.
- Apply STUCCOFACILE with a trowel, smoothing it over repeatedly to obtain a smooth surface, or use a putty knife to fill in cracks and hollows.
- Proceed to apply fixative, choosing on the basis of the type of paint to be used to finish.

Wooden surfaces:

- Sand lightly to remove loose wood fibres.
- Eliminate any peeling old paint and roughen all painted surfaces.
- Remove any resin with Nitro thinner 5170076.
- Smooth over flaws with STUCCOFACILE.
- Paint.

ИНСТРУКЦИИ ПО НАНЕСЕНИЮ

Ambient and base conditions:

Ambient temperature: Min. +5 C / Max.+35 C.

Ambient relative humidity: <80%.

Base temperature: Min. +5 C / Max. +35 C.

- Apply with a steel putty knife.
- Supplied ready to use.
- Clean utensils with water immediately after use.
- Approximate yield: varies greatly depending on the type of base. With a thickness of 300-350 micron, yield will be about 2 m2/kg. A preliminary test should be conducted on the wall to be treated to determine consumption.

КОЛЕРОВКА

ХРАНЕНИЕ

Maximum storage temperature: +30 °C

Minimum storage temperature: +5 °C

The product should be preferably used within 2 years from date of manufacture when stored in original unopened containers and in appropriate temperature conditions.

УКАЗАНИЯ ПО ТЕХНИКЕ БЕЗОПАСНОСТИ

Dir. 2004/42/EC not applicable

The product does not require labelling in accordance with 67/548/EEC and 1999/45/EC and its subsequent changes and updates. Use the product in accordance with the hygiene and safety regulations in force; avoid litter with the containers, allow the remains to dry well and treat as special waste. Keep out of the reach of children. Use in an airy place.

For further information consult the safety data sheet.

КРАТКОЕ ОПИСАНИЕ

Light stucco for walls and wood.

Application to prepared base of STUCCOFACILE stucco code 9560019 containing vinylversatic copolymer in a watery emulsion to level off walls and wood, both interior and exterior.

Supply and installation of material € per m2.

Il COLORIFICIO SAN MARCO garantisce, che rappresentata информация основана на лучших достижениях нашего опыта и научно-технических знаниях; однако невозможно взять на себя какую-либо ответственность за полученные результаты, так как условия применения не находятся под нашим непосредственным контролем. Рекомендуем всегда проверять пригодность материала в каждом отдельном случае. Данное техническое описание аннулирует и автоматически заменяет собой все предыдущие. По поводу любой другой технической информации обращаться к техническому персоналу COLORIFICIO SAN MARCO по телефону: +39 041 4569322.